

**SECTION 12 93 11
GRANITE SITE FURNISHINGS**

This guide specification utilizes recommendations and formats contained in references of the Construction Specifications Institute (CSI), including the CSI Practice Guides (formerly the Project Resource Manual), incorporating SectionFormat, PageFormat and MasterFormat, latest Editions, insofar as practicable.

This Section must be carefully reviewed and edited by the user to meet the Project requirements and should be coordinated with related Specification Sections and the Drawings.

Where Specification indicates information as "shown on Drawings" or similar phrases, the Drawings are required to show this information or the text needs to be modified appropriately.

Where Specification indicates bracketed text, e.g. [text], make appropriate selection and delete the remainder of text within additional brackets, highlighting, and bold face type.

Consult Dakota Granite Company for assistance in editing this Specification guide for the specific applications.

This Specification was current at the time of publication but is subject to change. Please confirm the accuracy of these specifications with the manufacturer prior to use.

For more information contact:

Dakota Granite Company
48391 150th Street
Milbank, SD 57252
Toll-Free: 1(800) 843-3333
Phone: (605) 432-5580
Fax: (605) 432-6155
www.dakotagranite.com
Email: dakota@dakgran.com

PART 1 - GENERAL

1.01 SUMMARY

- A. Section Includes:

SPECIFIER: Select applicable components in subparagraphs below.

01. Granite benches.
02. Granite tables.
03. Granite planters.
04. Granite fountains.
05. Installation accessories.
06. Miscellaneous materials.

1.02 RELATED REQUIREMENTS

- A. Drawings and general provisions of the Contract, including General and Supplementary Conditions and Division 01 Specification Sections, apply to this Section.
- B. Related Sections:

SPECIFIER: Select applicable Divisions or Sections in subparagraphs below related to the Work of this Section; adjust actual Section numbers and names as necessary.

- 01. [Division 03 Section "Cast-in-Place Concrete"] [Section 03 30 00 - Cast-In-Place Concrete];** for installation of anchor bolts cast in concrete.
- 02. [Division 22 Section "Plumbing"] [Section 22 10 00 - Plumbing Piping and Pumps];** for water supply and final connections to fountains.

1.03 DEFINITIONS

- A. Definitions contained in ASTM C119 apply to this Section.
- B. Metric conversions are shown in a table at the end of this Section.

1.04 REFERENCE STANDARDS

SPECIFIER: Use care when indicating the edition date of the referenced standards; these standards are subject to regular review, and updated accordingly. Edit list below to eliminate references not contained in the final text.

- A. ACI International/American Society of Civil Engineers/The Masonry Society (ACI/ASCE/TMS)
01. ACI 530.1/ASCE 6/TMS 602-02, Specification for Masonry Structures
- B. ASTM International (ASTM)
01. ASTM A276-10, Standard Specification for Stainless Steel Bars and Shapes
 02. ASTM A666-10, Standard Specification for Annealed or Cold-Worked Austenitic Stainless Steel Sheet, Strip, Plate and Flat Bar
 03. ASTM C114-11b, Standard Test Methods for Chemical Analysis of Hydraulic Cement
 04. ASTM C11911, Standard Terminology Relating to Dimension Stone
 05. ASTM C144-11, Standard Specification for Aggregate for Masonry Mortar
 06. ASTM C150-11, Standard Specification for Portland Cement
 07. ASTM C20706(2011), Standard Specification for Hydrated Lime for Masonry Purposes
 08. ASTM C27003, Standard Specification for Mortar for Unit Masonry
 09. ASTM C61511, Standard Specification for Granite Dimension Stone
 10. ASTM C1107-11, Standard Specification for Packaged Dry, Hydraulic-Cement Grout (Non-shrink)
 11. ASTM F59302(2008), Standard Specification for Stainless Steel Bolts, Hex Cap Screws, and Studs
 12. ASTM F59409e1, Standard Specification for Stainless Steel Nuts
- C. National Building Granite Quarries Association, Inc. (NBGQA)

NOTE: For the Specifier's convenience, a copy of the NBGQA document referenced below is published in the Dakota Granite "Architectural" Catalog, available upon request.

01. Specifications for Architectural Granite, 2010

1.05 ACTION AND INFORMATIONAL SUBMITTALS

SPECIFIER: Revise Section number in the paragraph below to match that used in the Project Manual.

- A. Submit in accordance with Section **[01 33 00] [Other]**:
 - 01. Product Data:
 - a. For each granite type and each manufactured product shown on Drawings or specified.
 - b. For each granite variety used on Project, include physical property data.
 - 02. Shop Drawings: Show fabrication and installation details for granite site furnishings.
 - a. Include dimensions and profiles of granite units.
 - 03. Granite Samples: Submit samples of each granite type required, exhibiting the full range of color characteristics expected in the completed Work.
 - a. Submit a minimum of 2 each, 12 inches by 12 inches (305 mm by 305 mm) in size, and in each color and finish specified.
 - b. In the case of more variegated granite, submit color photos in addition to the number of samples, to show the full range of color and markings.
 - 04. Other Samples:
 - a. Mortar: Full range of exposed color and texture; furnish 2 mortar keys in each color selected.
 - b. Grout: Full range of exposed color and texture; furnish 2 grout keys in each color selected.
 - c. Sealant: For each type and color of joint sealant selected.
 - 05. Certificates: Submit a letter of certification from the granite fabricator, stating the material being furnished is the specified material and there are sufficient reserves available to supply the Project and furnish replacement units if needed.
- B. Quality Assurance/Control Submittals:

SPECIFIER: Select Division 07 or Section 07 92 00 in subparagraph below; adjust actual Section number and name as necessary.

- 01. Sealant Compatibility Test Report: Submit test report from sealant manufacturer, in accordance with **[Division 07 Section "Joint Sealants"] [Section 07 92 00 - Joint Sealants]** stating that sealants will not stain granite.
- 02. Stone Test Reports:
 - a. Preliminary Test Reports: Submit test reports for proposed stones prior to final stone selection. Preliminary test reports shall be indicative of the granite to be proposed for the Project.
 - b. Material Test Reports: From a qualified independent testing agency.
 - 1) Provide reports for each granite type.
- 03. Qualification Data: Submit qualification data specified under Article 1.06 QUALITY ASSURANCE.
- C. Cold-Weather Procedures: Detailed description of methods, materials, and equipment.
- D. Hot-Weather Procedures: Detailed description of methods, materials, and equipment.

1.06 QUALITY ASSURANCE

- A. Compliance:
 - 01. Comply with the provisions of the Building Code, these specifications, and standards referenced in Article 1.04 REFERENCE STANDARDS, except where more stringent requirements are shown on the Drawings or specified herein.
- B. Granite Supply: Each type of granite shall come from a single quarry, with sufficient reserves to satisfy the requirements of the Project. The granite supplier shall have the capabilities to cut and finish the stone without delaying the Project.
- C. Fabricator Qualifications: Shop that employs skilled workers who custom-fabricate granite similar in material, design, and extent to that indicated for this Project, and whose work has resulted in applications with a record of successful in-service performance.
- D. Installer Qualifications: Experienced installer that has completed granite installations similar in material, design, and extent to that indicated for this Project.

1.07 DELIVERY, STORAGE, AND HANDLING

- A. Deliver, store and handle materials to prevent deterioration or damage.
 - 01. Carefully pack and load granite for shipment using reasonable care and customary precautions against damage in transit. Do not use material for blocking or packing, which may cause staining or discoloration.
 - 02. Stack granite on timber or platforms at least 4 inches (102 mm) above the ground. Use care to prevent staining or discoloration during storage.
 - 03. If storage is to be for a prolonged period, use polyethylene or other suitable plastic film placed between wood blocking and finished surfaces of completely dry stone. Ventilate under covers to prevent condensation.

04. Lift granite with wide-belt slings; do not use wire rope or ropes that might cause damage. Move granite, if required, using dollies with cushioned wood supports.
05. Properly store cementitious materials on elevated platforms, under cover, and in dry location.
06. Store aggregates where grading and other required characteristics can be maintained and contamination avoided.
07. Store polymer additives in unopened containers and protected from freezing.
08. Store installation accessories, including metal items, to prevent corrosion and contamination.

1.08 FIELD CONDITIONS

- A. Cold-Weather Requirements: Comply with ACI 530.1/ASCE 6/TMS 602.
- B. Hot-Weather Requirements: Comply with ACI 530.1 ASCE 6/TMS 602.

PART 2 - PRODUCTS

2.01 GRANITE SOURCE

- A. Varieties and Source: Subject to compliance with requirements, provide granite from the following source:
 01. Granite Source: Dakota Granite Company; 1(605) 432-5580.
- B. Substitutions: Suppliers seeking approval of their products are required to comply with the Owner's Instructions to Bidders.
- C. Granite Source Examination: Make quarried blocks available for examination by Architect.

2.02 GRANITE MATERIAL

- A. Granite: ASTM C615; match Architects's samples.

2.03 BENCHES

SPECIFIER: Indicate applicable characteristics in subparagraphs below; add information as necessary to meet Project requirements.

- A. Granite Benches:
 01. Granite Variety: **[Insert granite variety]**.
 02. Finish: **[Brushed] [Honed] [Polished] [Sandblasted] [Split face] [Thermal] [Water jet] [Other]**.
 03. Size and Shape: Refer to Drawings.
- B. Bench Tops:
 01. Nominal Thickness: **[1 1/2 inches (40 mm)] [2 inches (51 mm)]**.
 02. Edge: **[Straight, slightly eased at corners] [Refer to Drawings]**.
 03. Corner Detail: **[Square, slightly eased] [Refer to Drawings]**.
 04. Bottom Surface Finish: Sawn.
- C. Bench Pedestals:
 01. Nominal Thickness: 4 inches (102 mm).
 02. Edge: **[Straight, slightly eased at corners] [Refer to Drawings]**.

2.04 TABLES

SPECIFIER: Indicate applicable characteristics in subparagraphs below; add information as necessary to meet Project requirements.

- A. Granite Tables:
 01. Granite Variety: **[Insert granite variety]**.
 02. Finish: **[Antique] [Honed] [Polished] [Sandblasted] [Split face] [Thermal] [Water jet] [Other]**.
 03. Size and Shape: Refer to Drawings.
- B. Table Tops:
 01. Nominal Thickness:
 - a. Unless otherwise indicated, provide not less than the following thicknesses: **[1 inch (25 mm)] [1 1/4 inches (32 mm)] [1 1/2 inches (38 mm)] [2 inches (51 mm)]**.
 02. Edge: **[Straight, slightly eased at corners] [Refer to Drawings]**.
 03. Corner Detail: **[Square, slightly eased] [Refer to Drawings]**.
 04. Bottom Surface Finish: Sawn.

- C. Table Pedestals:
 - 01. Nominal Thickness: 4 inches (102 mm).
 - 02. Edge: **[Straight, slightly eased at corners] [Refer to Drawings]**.

2.05 PLANTERS

SPECIFIER: Indicate applicable characteristics in subparagraphs below; add information as necessary to meet Project requirements.

- A. Granite Planters:
 - 01. Granite Variety: **[Insert granite variety]**.
 - 02. Finish: **[Honed] [Polished] [Sandblasted] [Split face] [Thermal] [Water jet] [Other]**.
 - 03. Size and Shape: Refer to Drawings.
 - 04. Nominal Thickness:
 - a. Unless otherwise indicated, provide not less than the following thicknesses: **[1 inch (25 mm)] [11/4 inches (32 mm)] [11/2 inches (38 mm)] [2 inches (51 mm)]**.
 - 05. Provide holes in base of planter to permit drainage. Locate holes to be least conspicuous, yet allow free drainage.
- B. Inner Container: Provide manufacturer's standard container for placing inside of planters, to reduce staining of granite due to soil contamination and moisture; construct container from **[galvanized steel sheet] [rigid plastic]**. Provide holes in base of container to permit drainage.
- C. Installation Method: Free-standing.

2.06 FOUNTAINS

- A. Granite Fountains:
 - 01. Granite Variety: **[Insert granite variety]**.
 - 02. Finish: **[Honed] [Polished] [Sandblasted] [Split face] [Thermal] [Water jet] [Other]**.
 - 03. Size and Shape: Custom size and shape as indicated on Drawings.
- B. Water Piping, Fittings, and Drains: Provide internal fountain components for final connection to site or building water supply.

2.07 MORTAR MATERIALS

- A. Portland Cement: ASTM C150, Type I or Type II, except Type III may be used for cold-weather construction.
 - 01. Provide natural color or white cement as required to produce mortar color indicated.

SPECIFIER: Retain subparagraph below if recommended by stone source to limit staining.

- 02. Low-Alkali Cement: Not more than 0.60 percent total alkali when tested according to ASTM C114.
- B. Hydrated Lime: ASTM C207.
- C. Portland Cement-Lime Mix: Packaged blend of portland cement complying with ASTM C150, Type I or III, and hydrated lime complying with ASTM C207; provide products by one of the following:
 - 01. Essroc, Italcementi Group
 - 02. Holcim (US), Inc.
 - 03. Lafarge North America
 - 04. Lehigh Cement Company
- D. Mortar Pigments: Natural and synthetic iron oxides with a record of satisfactory performance in mortar, and containing no carbon black; provide products by one of the following:
 - 01. Davis Colors
 - 02. Solomon Colors
- E. Colored Cement Product: Packaged blend made from portland cement and lime and mortar pigments, all complying with specified requirements, and containing no other ingredients.
 - 01. Formulate blend as required to produce color indicated or, if not indicated, as selected from manufacturer's standard colors.
 - 02. Do not exceed 10 percent of Portland cement by weight.
 - 03. Do not exceed 5 percent of masonry cement or mortar cement by weight.
 - 04. Mix mortar to match Architect's sample.
 - 05. Provide products by one of the following:

- a. Holcim (US), Inc.
 - b. Lafarge North America
 - c. Lehigh Cement Company
- F. Aggregate: ASTM C144.
- G. Latex Additive: Acrylic-resin water emulsion recommended by additive manufacturer for use with field-mixed Portland cement mortar bed; provide products by one of the following:
- 01. Bonsal
 - 02. Bostik Findley, Inc.
 - 03. C-Cure
 - 04. Custom Building Products
 - 05. DAP, Inc.
 - 06. Laticrete International, Inc.
 - 07. MAPEI Corp.
 - 08. TEC Specialty Construction Brands; H. B. Fuller Company.
- H. Water: Potable.

2.08 GROUT

- A. Non-shrink, Nonmetallic Grout: ASTM C1107; recommended in writing by grout manufacturer, for exterior applications.

SPECIFIER: Select one of 2 subparagraphs below; indicate actual color(s) if known.

- 01. Color: Selected by the Architect from manufacturer's **[standard colors] [full range of colors]**.
 - 01. Color: **[Match granite] [Match Architect's samples]**.
- B. Water: Potable.

2.09 ANCHORS AND FASTENERS

- A. Stone Anchors: Anchors designed to engage kerfs or holes in stone trim and holes for anchor bolts for fastening to substrates or framing.
- 01. Anchor Material: Stainless steel, ASTM A666, Type 304.
 - 02. Dowels and Pins Material: Stainless steel, ASTM A276, Type 304.
- B. Post-Installed Anchor Bolts: Provide the following for installation into concrete:
- 01. Expansion anchors.
 - 02. Stainless Steel Bolts: ASTM F593, Alloy Group 1 or 2.
 - 03. Stainless Steel Nuts: ASTM F594, Alloy Group 1 or 2.
 - 04. Anchor Material: ASTM A666 or ASTM A276, Type 304 or 316.

2.10 GRANITE FABRICATION

- A. Fabricate granite to comply with requirements indicated and with NBGQA's "Specifications for Architectural Granite".
- B. Select granite for intended use to prevent fabricated units from containing cracks, seams, and starts that could impair structural integrity or function.
- C. Cut granite from one block or contiguous, matched blocks in which natural markings occur.
- D. Fabricate granite in sizes and shapes required to comply with requirements indicated, including details on Drawings and final shop drawings.
- E. Finish exposed faces and edges of granite (except sawn reveals), to comply with requirements indicated for finish and to match approved samples and mock-ups.
- 01. Exposed Ends: Finish exposed ends to match exposed face, unless otherwise indicated.
 - 02. Arises: Remove the sharp edge from arises to slightly blunt edge and to reduce chipping of the finished edge.
- F. Dress joints straight and at 90-degree angle to face. Shape beds to fit supports.
- G. Anchor Provisions: Cut and drill sink provisions and holes in stone for anchors, fasteners, supports, and lifting devices as indicated or needed to set stone in place.
- 01. Allow room for expansion of the anchoring devices where necessary.

SPECIFIER: Select desired joint width in paragraph below.

- H. Joint Width: Cut granite to produce uniform joints **[3/8 inch (10 mm)] [other] [as shown on Drawings]**.
- I. Provide reveals, reglets, openings, and similar features as required to accommodate adjacent work.
- J. Fabricate molded work, including washes and drips, to produce uniform stone shapes, with precisely formed arises slightly eased, and matching profile at joints between units.

- K. Inspect granite at fabrication plant for compliance with requirements for appearance, material, and fabrication, prior to delivery to the Project site. Replace defective units which do not comply before shipment.
- L. Fabrication Tolerances:
 - 01. Granite thickness 2 inches (51 mm) or less: Plus or minus 1/16 inch (1.5 mm) of the nominal thickness.
 - 02. Granite thicknesses greater than 2 inches (51 mm): Plus or minus 1/8 inch (3 mm) of the nominal thickness.
 - 03. Overall face size: Plus or minus 1/16 inch (1.5 mm) in both height and width.
 - 04. Out of square: Plus or minus 1/8 inch (3 mm) difference of diagonals.

2.11 GRANITE GRAPHICS AND INSCRIPTIONS

- A. Carve and cut graphics and inscriptions in accordance with final shop drawings. Use skilled stone carvers experienced in the successful performance of work similar to that indicated.

SPECIFIER: Select one of the following paragraphs below for graphics and inscriptions incorporation; consult granite supplier for recommendations.

- B. Abrasively etch graphics and inscriptions in accordance with final shop drawings.
- C. Laser etch graphics and inscriptions in accordance with final shop drawings.

2.12 MORTAR AND GROUT MIXES AND MIXING

- A. Pre-blended, Dry Mortar Mix: Furnish dry mortar ingredients in the form of a pre-blended mix.
 - 01. Measure quantities by weight to ensure accurate proportions, and thoroughly blend ingredients before delivering to Project site.
- B. Mortar for Stone Masonry: Comply with ASTM C270 Type S, Proportion Specification.
- C. Latex-Modified Portland Cement Setting Mortar: Proportion and mix portland cement, aggregate, and latex additive to comply with latex-additive manufacturer's written instructions.
- D. Pigmented Mortar: Use colored cement product or select and proportion pigments with other ingredients to produce color required. Do not add pigments to colored cement products.
 - 01. Do not exceed 10 percent of Portland cement by weight.
 - 02. Do not exceed 5 percent of masonry cement or mortar cement by weight.
 - 03. Mix mortar to match Architect's sample.
- E. Grout: Comply with manufacturer's written instructions.

PART 3 - EXECUTION

3.01 EXAMINATION

- A. Examine surfaces indicated to receive granite site furnishings and conditions under which granite site furnishings will be installed, for compliance with requirements for installation.
 - 01. Review requirements for correct and level finished grade, mounting surfaces and other conditions affecting performance.
 - 02. Proceed with installation only after unsatisfactory conditions have been corrected.

3.02 INSTALLATION - GENERAL

- A. Comply with manufacturer's written installation instructions. Complete field assembly where required.
- B. Install site furnishings level, plumb, true and located where indicated on Drawings.
- C. Cleaning: Clean granite site furnishings after setting and grouting is complete, so that surfaces are free of foreign matter.
 - 01. Remove grout residue from exposed surfaces as soon as possible. Clean grout smears and haze from granite using granite producer's and grout manufacturer's written instructions, but no sooner than 10 days after installation. Use only cleaners recommended by granite producer and grout manufacturer and only after determining that cleaners are safe to use by testing on samples of granite and other surfaces to be cleaned. Flush surfaces with clean water before and after cleaning.

3.03 ADJUSTING

- A. Inspect site furnishing after completion of installation.
- B. Remove granite site furnishing components and related work with the following defects, and replace with new units, unless otherwise specified herein:
 - 01. Broken, chipped, permanently stained, and otherwise damaged granite units.
 - 02. Granite site furnishing components not complying with other requirements indicated.

- C. Patching: Minor patching in small areas may be acceptable if the repair does not distract from the overall appearance of the finished Project.
 - 01. Repair granite using methods recommended by granite producer.
 - 02. The Architect will make final decision on acceptance of patched granite, at their discretion.

END OF SECTION

NOTE: The following metric conversions shall apply where English measurements are indicated in the text:

1/64 inch	(0.40 mm)
1/32 inch	(0.80 mm)
1/16 inch	(1.5 mm)
1/8 inch	(3 mm)
3/16 inch	(5 mm)
1/4 inch	(6 mm)
5/16 inch	(8 mm)
3/8 inch	(10 mm)
1/2 inch	(13 mm)
5/8 inch	(16 mm)
3/4 inch	(19 mm)
13/16 inch	(20 mm)
1 inch	(25 mm)
13/16 inches	(30 mm)
11/4 inches	(32 mm)
11/2 inches	(38 mm)
15/8 inches	(41 mm)
2 inches	(51 mm)
3 inches	(76 mm)
4 inches	(102 mm)
6 inches	(152 mm)
7 inches	(178 mm)
8 inches	(203 mm)
10 inches	(254 mm)
12 inches	(305 mm)
16 inches	(406 mm)
18 inches	(457 mm)
24 inches	(610 mm)(0.6 m)
48 inches	(1220 mm)(1.2 m)
8 feet	(2440 mm)(2.4 m)
10 feet	(3 m)
20 feet	(6 m)
40 feet	(12 m)